


EXPOLINE



Product Information

Usage classification	EN ISO 10874 EN 685		23 - 32 - 41
Wear layer	EN ISO 24340 EN 429		0,40 mm
Total thickness	EN ISO 24346 EN 428		2,00 mm
Total weight	EN ISO 23997 EN 430		1600 g/m ²
Standard widths	EN ISO 24341 EN 426		2 - 3 - 4m
Standard length	EN ISO 24341 EN 426		30m

Technical Information

Light stability	EN ISO 105 B02		≥ 6
Dimensional Stability	EN ISO 23999 EN 434		≤ 0,40 %
Underfloor heating	EN 12667		Suitable
Residual Indentation	EN ISO 24343-2 EN 433		≤ 0,20 mm
Impact sound	EN ISO 717/2		Δ Lw 10 dB
Castor chair	EN ISO 4918 EN 425		Suitable
Reaction to fire	EN 13501-1		Bfl/S1
Slip resistance	DIN 51130		R10
Dynamic coefficient of friction	EN 13893		> 0,6